




TEST REPORT

Test Report # 17H-003209 Date of Report Issue: August 24, 2017
 Date of Sample Received: April 28, 2017 Pages: Page 1 of 41

CLIENT INFORMATION:

Company: Polyconcept Hong Kong Ltd
 Recipient: Patrick Lam
 Recipient Email: patrick.lam@polyconceptgbs.com



SAMPLE INFORMATION:

Description:	Refer to Page 2 to 4	Purchase Order Number:	-
Assortment:	-	Toy Co./Agency:	-
Article No.:	Refer to Page 2 to 4	Country of Origin:	China
Vendor Name:	10647	Labeled Age Grade:	-
Country of Distribution:	-	Requested Age Grade:	-
Quantity Submitted:	Refer to Page 2 to 4	Tested Age Grade:	-
Testing Period:	07/19/2017 – 08/11/2017		

OVERALL RESULT:

PASS

Refer to page 5 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka
 Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street• Kwun Tong• Kowloon •Hong Kong •Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**ARTICLE NO./QUANTITY SUBMITTED DETAILED:**

Description	Article No.	Qty.
The 16-oz. Party Cup	SM-6688BK	10 pcs
	SM-6688NOR	10 pcs
	SM-6688NY	10 pcs
	SM-6688YW	10 pcs
	SM-6688RD	10 pcs
	SM-6688RYL	10 pcs
	SM-6688GR	10 pcs
	SM-6688WH	10 pcs
Iceberg 16-oz. Tumbler with Straw	SM-6635TBL	10 pcs
	SM-6635TLG	10 pcs
	SM-6635TRE	10 pcs
	SM-6635TSM	12 pcs
	SM-6635TOR	10 pcs
	SM-6635TPU	10 pcs
	SM-6635CL	10 pcs
Surfside 26-oz. Sports Bottle	SM-6804TGR	10 pcs
	SM-6804TBK	10 pcs
	SM-6804BK	10 pcs
	SM-6804TRE	10 pcs
	SM-6804CL	10 pcs
	SM-6804TBL	10 pcs
Glacier 20-oz. Tumbler with Straw - TRANSPARENT LID	SM-6625CL	10 pcs
Glacier 20-oz. Tumbler with Straw - TANSSPARENT BLUE LID	SM-6625TRBL	10 pcs
Florida Flyer	SM-7435RE	10 pcs
	SM-7435NG	10 pcs
	SM-7435YE	10 pcs
	SM-7435WH	10 pcs
	SM-7435BL	10 pcs
	SM-7435BK	10 pcs
	SM-7435TGR	10 pcs
	SM-7435TBL	10 pcs
Bali 30-oz. Sports Bottle	SM-6805WH	10 pcs
	SM-6805CL	9 pcs

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**ARTICLE NO./QUANTITY SUBMITTED DETAILED:**

Description	Article No.	Qty.
Easy Squeezy 24oz Sports Bottle -Crystal	SM-6523CL	10 pcs
	SM-6523TRBL	10 pcs
	SM-6523TGR	10 pcs
	SM-6523TBK	10 pcs
	SM-6523TRE	10 pcs
Stay Cool 32-oz. Sports Bottle	SM-6886RYL	10 pcs
	SM-6886CL	10 pcs
	SM-6886SGL	10 pcs
Rally 22-oz. Stadium Cup	SM-6648GR	10 pcs
	SM-6648BL	10 pcs
	SM-6648RE	10 pcs
	SM-6648BK	10 pcs
	SM-6648MA	10 pcs
	SM-6648WH	10 pcs
	SM-6648NG	10 pcs
Marley 32-oz. Sports Bottle	SM-6865SM	40 pcs
	SM-6865SGL	40 pcs
	SM-6865BL	40 pcs
	SM-6865RD	40 pcs
	SM-6865TBK	40 pcs
Liberty 20-oz. Square Mason Jar	SM-6927LIDBL	10 pcs
	SM-6927LIDCL	10 pcs
	SM-6927JARCL	50 pcs
	SM-6927LIDGR	10 pcs
	SM-6927LIDRD	10 pcs
	SM-6927LIDSM	10 pcs
Fruit Infuser 25-oz. Sports Bottle	SM-6870CL	40 pcs

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street• Kwun Tong• Kowloon •Hong Kong •Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**ARTICLE NO./QUANTITY SUBMITTED DETAILED:**

Description	Article No.	Qty.
Rally 16-oz. Stadium Cup	SM-6645NG	10 pcs
	SM-6645WH	10 pcs
	SM-6645BL	10 pcs
	SM-6645BK	10 pcs
	SM-6645MA	10 pcs
	SM-6645RE	10 pcs
	SM-6645NBL	10 pcs
Bayside 16-oz. Double Wall Tumbler w/Lid	SM-6692CL	10 pcs
Easy Squeezy 24oz Sports Bottle - Spirit	SM-6513RBL	10 pcs
	SM-6513RE	10 pcs
	SM-6513NBL	10 pcs
	SM-6513BK	10 pcs
Glacier 20-oz. Tumbler with Straw	SM-6625TRE	10 pcs
	SM-6625TBK	10 pcs
	SM-6625TLGR	10 pcs

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street• Kwun Tong• Kowloon •Hong Kong •Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	Client's Requirement, Bisphenol A [#]
PASS	FDA 21 CFR 177.1520, Polyethylene
PASS	FDA 21 CFR 177.1520, Polypropylene Copolymers
PASS	FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers
PASS	Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11+12	13+14+15	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	16+17+18	19+20+21	22+23+24	25+26+27	28+29+30	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	37+38+39	40+41+42	43+44+45	46+47+48	49+50+51	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	52+53+54	55+56	57+58	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	---	---	100
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		46+49+51	53+54+55	56+57	---	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		46+49+51	53+54+55	56+57	---	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****Client's Requirement, Bisphenol A**Test Method: AI | ANSECO Method[#]

Analytical Method: Liquid Chromatography with Fluorescence Detection

Specimen No.		1	2	3	4	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		5	6	7	8	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		9	10	11	12	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		13	14	15	16	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not Detected (Reporting Limit = 1 ppm)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****Client's Requirement, Bisphenol A**Test Method: AI | ANSECO Method[#]

Analytical Method: Liquid Chromatography with Fluorescence Detection

Specimen No.		17	18	19	20	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		21	22	23	24	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		25	26	27	28	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		29	30	31	32	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not Detected (Reporting Limit = 1 ppm)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****Client's Requirement, Bisphenol A**Test Method: AI | ANSECO Method[#]

Analytical Method: Liquid Chromatography with Fluorescence Detection

Specimen No.	33	34	35	36	Limit (ppm)
Test Item CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA) 80-05-7	ND	ND	ND	ND	ND
Conclusion	PASS	PASS	PASS	PASS	

Specimen No.	37	38	39	40	Limit (ppm)
Test Item CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA) 80-05-7	ND	ND	ND	ND	ND
Conclusion	PASS	PASS	PASS	PASS	

Specimen No.	41	42	43	44	Limit (ppm)
Test Item CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA) 80-05-7	ND	ND	ND	ND	ND
Conclusion	PASS	PASS	PASS	PASS	

Specimen No.	45	58	---	---	Limit (ppm)
Test Item CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA) 80-05-7	ND	ND	---	---	ND
Conclusion	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not Detected (Reporting Limit = 1 ppm)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			1	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.942	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	1.9	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	ND	1.0	11.3
Conclusion			PASS		

Specimen No.			2	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.940	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	ND	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	ND	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			3	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.940	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	ND	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	ND	1.0	11.3
Conclusion			PASS		

Specimen No.			4	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.946	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	ND	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	ND	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			30	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.898	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	2.9	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	5.8	1.0	11.3
Conclusion			PASS		

Specimen No.			31	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.912	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	2.9	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	5.7	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			32	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.923	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.2	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	5.1	1.0	11.3
Conclusion			PASS		

Specimen No.			33	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.900	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.4	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	5.8	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			34	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.920	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.9	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	4.5	1.0	11.3
Conclusion			PASS		

Specimen No.			35	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.900	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.7	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	5.1	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			36	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.895	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.2	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	4.6	1.0	11.3
Conclusion			PASS		

Specimen No.			37	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.903	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.7	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	4.6	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			38	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.900	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.7	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	4.7	1.0	11.3
Conclusion			PASS		

Specimen No.			39	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	4.0	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	4.7	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			40	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.5	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	3.8	1.0	11.3
Conclusion			PASS		

Specimen No.			41	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.3	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	3.9	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			42	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.7	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	6.9	1.0	11.3
Conclusion			PASS		

Specimen No.			43	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.893	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	4.0	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	6.6	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polyethylene**

Test Method: FDA 21 CFR 177.1520

Specimen No.			44	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.894	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	4.1	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	5.7	1.0	11.3
Conclusion			PASS		

Specimen No.			45	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.893	NA	0.85 - 1.00
n-Hexane extractive (% m/m)	50°C	2 hours	3.8	0.4	5.5
Xylene extractive (% m/m)	Reflux	2 hours	5.0	1.0	11.3
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celcius

g/cc = Grams per cubic centimeter

%m/m= Percent by mass

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			5		
Test Item	Test Condition		Result	RL	Limit
	Temp.	Duration			
Density (g/cc)	NA	NA	0.913	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	1.6	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	4.6	1	30
Conclusion			PASS		

Specimen No.			6		
Test Item	Test Condition		Result	RL	Limit
	Temp.	Duration			
Density (g/cc)	NA	NA	0.904	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.3	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	5.9	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			7	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.900	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.1	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	8.1	1	30
Conclusion			PASS		

Specimen No.			8	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.900	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.9	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	8.1	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			9	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.903	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.3	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	8.2	1	30
Conclusion			PASS		

Specimen No.			10	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.2	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	7.1	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			11		
Test Item	Test Condition		Result	RL	Limit
	Temp.	Duration			
Density (g/cc)	NA	NA	0.895	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.1	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	7.2	1	30
Conclusion			PASS		

Specimen No.			12		
Test Item	Test Condition		Result	RL	Limit
	Temp.	Duration			
Density (g/cc)	NA	NA	0.901	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	1.2	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	6.9	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			13	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	1.0	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	8.3	1	30
Conclusion			PASS		

Specimen No.			14	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.893	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.4	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	5.6	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			15	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.894	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	3.2	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	6.4	1	30
Conclusion			PASS		

Specimen No.			16	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.895	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.7	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	5.6	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			17		
Test Item	Test Condition		Result	RL	Limit
	Temp.	Duration			
Density (g/cc)	NA	NA	0.893	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.0	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	5.8	1	30
Conclusion			PASS		

Specimen No.			18		
Test Item	Test Condition		Result	RL	Limit
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.6	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	4.9	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			19	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	2.0	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	8.0	1	30
Conclusion			PASS		

Specimen No.			20	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.892	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50°C	2 hours	3.7	0.4	5.5
Xylene extractive (% w/w)	25°C	1 hour	6.3	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.		21		Result	RL	Limit
Test Item	Test Condition					
	Temp.	Duration				
Density (g/cc)	NA	NA	0.891	NA	0.85 – 1.00	
n-Hexane extractive (% w/w)	50°C	2 hours	3.3	0.4	5.5	
Xylene extractive (% w/w)	25°C	1 hour	7.2	1	30	
Conclusion			PASS			

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

**DETAILED RESULTS:****FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers**

Test Method: FDA 21 CFR 177.1630

Specimen No.			22	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Specimen No.			23	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Specimen No.			24	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers**

Test Method: FDA 21 CFR 177.1630

Specimen No.			25	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Specimen No.			26	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Specimen No.			27	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers**

Test Method: FDA 21 CFR 177.1630

Specimen No.			28	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Specimen No.			29	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

**DETAILED RESULTS:****Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11+12	13+14+15	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	16+17+18	19+20+21	22+23+24	25+26+27	28+29+30	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	37+38+39	40+41+42	43+44+45	46+47+48	49+50+51	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	52+53+54	55+56	57+58	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	---	---	90
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Blue plastic (HDPE)	Body (SM-6513RBL style)
2	Red plastic (HDPE)	Body (SM-6513RE style)
3	Deep blue plastic (HDPE)	Body (SM-6513NBL style)
4	Black plastic (HDPE)	Body (SM-6513BK style)
5	Translucent plastic (PP-co)	Spout (all SM-6513/ all SM-6523 styles)
6	Dull blue plastic (PP-co)	Lid (SM-6513RBL style)
7	Dull red plastic (PP-co)	Lid (SM-6513RE style)
8	Dull deep blue plastic (PP-co)	Lid (SM-6513NBL style)
9	Dull black plastic (PP-co)	Lid (SM-6513BK/ SM-6523TBK/ SM-6804CL/ SM-6804BK/ all SM-6805/ SM-6870CL styles); flip (SM-6804CL/ SM-6804BK styles); spout (all SM-6805/ all SM6886 styles)
10	Transparent plastic (PP-co)	Lid (SM-6523CL/ all SM-6865/ all SM-6886/ SM-6927LIDCL/ SM-6625CL/ SM-6635CL styles); infuser (SM-6870CL/ SM-6886CL styles); connector (SM-6870CL/ all SM-6886 styles); straw (SM-6865GL/ SM-6625CL/ SM-6635CL styles); spout (SM-6870CL style); ring of straw (all SM-6865/ all SM-6625/ all SM-6635 styles)
11	Transparent blue plastic (PP-co)	Lid (SM-6523TRBL/ SM-6804TBL/ SM-6927LIDBL styles); flip (SM-6804TBL style)
12	Transparent green plastic (PP-co)	Lid (SM-6523TGR/ SM-6804TGR/ SM-6927LIDGR styles); flip (SM-6804TGR style)
13	Transparent red plastic (PP-co)	Lid (SM-6523TRE/ SM-6804TRE/ SM-6927LIDRD/ SM-6625TRE/ SM-6635TRE styles); flip (SM-6804TRE style); spout (SM-6865RD style); straw (SM-6865RD/ SM-6625TRE/ SM-6635TRE styles)
14	Transparent black plastic (PP-co)	Lid (SM-6804TBK/ SM-6927LIDSM/ SM-6625TBK/ SM-6635TSM styles); straw (SM-6865SM/ SM-6865TBK/ SM-6625TBK/ SM-6635TSM styles); flip (SM-6804TBK style); spout (SM-6865SM/ SM-6865TBK styles)
15	Transparent turquoise plastic (PP-co)	Spout (SM-6865GL style); infuser (SM-6886SGL style)
16	Transparent deep blue plastic (PP-co)	Spout (SM-6865BL style)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
17	Dull transparent blue plastic (PP-co)	Straw (SM-6865BL/ SM-6625TRBL/ SM-6635TBL styles); infuser (SM-6886RYL style); lid (SM-6625TRBL/ 6635TBL styles)
18	Matt transparent green plastic (PP-co)	Straw (SM-6625TLGR/ SM-6635TLG styles)
19	Bright transparent green plastic (PP-co)	Lid (SM-6625TLGR/ SM-6635TLG styles)
20	Transparent orange plastic (PP-co)	Straw/ lid (SM-6635TOR style)
21	Transparent purple plastic (PP-co)	Straw/ lid (SM-6635TPU style)
22	Clear plastic (PET)	Body (SM-6523CL/ SM-6804CL/ SM-6805CL/ SM-6870CL/ SM-6865SM/ SM-6865BL/ all SM-6886/ SM-6927JARCL/ SM-6692CL styles); lid (SM-6692CL style)
23	Clear blue plastic (PET)	Body (SM-6523TRBL/ SM-6804TBL styles)
24	Clear green plastic (PET)	Body (SM-6523TGR/ SM-6804TGR styles)
25	Clear black plastic (PET)	Body (SM-6523TBK/ SM-6804TBK/ SM-6865TBK styles)
26	Clear red plastic (PET)	Body (SM-6523TRE/ SM-6804TRE/ SM-6865RD styles)
27	Matt black plastic (PET)	Body (SM-6804BK style)
28	White plastic (PET)	Body (SM-6805WH style)
29	Clear turquoise plastic (PET)	Body (SM-6865GL style)
30	Bright green plastic (LDPE)	Cup (SM-6645NG style)
31	Dull white plastic (LDPE)	Cup (SM-6645WH/ SM-6648WH styles); inner wall (all SM-6688 styles)
32	Matt blue plastic (LDPE)	Cup (SM-6645BL/ SM-6648BL styles)
33	Off black plastic (LDPE)	Cup (SM-6645BK/ SM-6648BK styles)
34	Bright red plastic (LDPE)	Cup (SM-6645RE/ SM-6648RE styles); flyer (SM-7435RE style)
35	Dark blue plastic (LDPE)	Cup (SM-6645NBL style)
36	Light green plastic (LDPE)	Cup (SM-6648NG style)
37	Green plastic (LDPE)	Cup (SM-6648GR style)
38	Dark purple plastic (LDPE)	Cup (SM-6645MA/ SM-6648MA styles)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
39	Dull clear plastic (LDPE)	Cup (all SM-6625 styles); inner/ outer wall (SM-6635CL style)
40	Dull clear blue plastic (LDPE)	Inner/ outer wall (SM-6635TBL style)
41	Dull clear green plastic (LDPE)	Inner/ outer wall (SM-6635TLG style)
42	Dull clear red plastic (LDPE)	Inner/ outer wall (SM-6635TRE style)
43	Dull clear black plastic (LDPE)	Inner/ outer wall (SM-6635TSM style)
44	Clear purple plastic (LDPE)	Inner/ outer wall (SM-6635TPU style)
45	Clear orange plastic (LDPE)	Inner/ outer wall (SM-6635TOR style)
46	Off black plastic	Cup (SM-6645BK/ SM-6648BK styles); outer wall (SM-6688BK style); flyer (SM-7435BK style)
47	Orange plastic	Outer wall (SM-6688NOR style)
48	Darkblue plastic	Cup (SM-6645NBL style); outer wall (SM-6688NY style)
49	Yellow plastic	Outer wall (SM-6688YW style); flyer (SM-7435YE style)
50	Deep red plastic	Outer wall (SM-6688RD style)
51	Matt blue plastic	Cup (SM-6645BL/ SM-6648BL styles); outer wall (SM-6688RYL style); flyer (SM-7435BL style)
52	Dark green plastic	Outer wall (SM-6688GR style)
53	Bright red plastic	Cup (SM-6645RE/ SM-6648RE styles); flyer (SM-7435RE style)
54	Light green plastic	Cup (SM-6648NG style); flyer (SM-7435NG style)
55	Dull white plastic	Cup (SM-6645WH/ SM-6648WH styles); inner wall (all SM-6688 styles); outer wall (SM-6688WH style); flyer (SM-7435WH style)
56	Dull transparent green plastic	Flyer (SM-7435TGR style)
57	Matt clear blue plastic	Flyer (SM-7435TBL style)
58	Dull translucent plastic	Slider (SM-6692CL style)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



SAMPLE PHOTO:



ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street• Kwun Tong• Kowloon •Hong Kong •Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



SAMPLE PHOTO:



ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street• Kwun Tong• Kowloon •Hong Kong •Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



SAMPLE PHOTO:



ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street• Kwun Tong• Kowloon •Hong Kong •Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



SAMPLE PHOTO:



-End Report-